

Appendix A:

Abstracts of two references cited in WO 01/96847, Zhou et al.

- 1) Abstract of Morales and Lieber, Science, 279, 209-211, 1998
- 2) Abstract of Zhang et al., Appl. Phys. Lett, 72, 15, 1835-1837, 1998

Science

AAAS

Magazine

News

Signaling

Careers

Multimedia

Collections

[Current Issue](#)

[Previous Issues](#)

[Science Express](#)

[Science Products](#)

[My Science](#)

[Home](#) > [Science Magazine](#) > [9 January 1998](#) > Morales et al pp. 208 - 211

Science 9 January 1998:

Vol. 279, no. 5348, pp. 208 - 211

DOI: 10.1126/science.279.5348.208

REPORTS

A Laser Ablation Method for the Synthesis of Crystalline Semiconductor Nanowires

Alfredo M. Morales, Charles M. Lieber *

A method combining laser ablation cluster formation and vapor-liquid-solid (VLS) growth was developed for the synthesis of semiconductor nanowires. In this process, laser ablation was used to prepare nanometer-diameter catalyst clusters that define the size of wires produced by VLS growth. This approach was used to prepare bulk quantities of uniform single-crystal silicon and germanium nanowires with diameters of 6 to 20 and 3 to 9 nanometers, respectively, and lengths ranging from 1 to 30 micrometers. Studies carried out with different conditions and catalyst materials confirmed the central details of the growth mechanism and suggest that well-established phase diagrams can be used to predict rationally catalyst materials and growth conditions for the preparation of nanowires.


A. M. Morales, Department of Chemistry and Chemical Biology, Harvard University, Cambridge, MA 02138, USA.

C. M. Lieber, Department of Chemistry and Chemical Biology, and Division of Engineering and Applied Sciences, Harvard University, Cambridge, MA 02138, USA.

* To whom correspondence should be addressed. E-mail: cml@cmliris.harvard.edu

[Read the Full Text](#)

Applied Physics Letters

Appl. Phys. Lett. / Volume 72 / Issue 15 / CONDENSED MATTER: STRUCTURE, MECHANICAL AND THERMA...  PRINT PAGE

Silicon nanowires prepared by laser ablation at high temperature

Appl. Phys. Lett. 72, 1835 (1998); DOI:10.1063/1.121199

Issue Date: 13 April 1998

Y. F. Zhang, Y. H. Tang, N. Wang, D. P. Yu, C. S. Lee, I. Bello, and S. T. Lee

Department of Physics and Materials Science, City University of Hong Kong, Kowloon, Hong Kong

Silicon nanowires have been synthesized in high yield and high purity by using a high-temperature laser-ablation method with growth rates ranging from 10 to 80 $\mu\text{m/h}$. Transmission electron microscopic investigation shows that the nanowires are crystalline Si, and have diameters ranging from 3 to 43 nm and length up to a few hundreds microns. Twins and stacking faults have been observed in the Si core of the nanowires. The lattice structure and constant of the nanowires as determined from x-ray diffraction (XRD) are nearly identical to those of bulk Si, although the relative XRD peak intensities are different from those of randomly oriented Si crystallites. Raman scattering from the nanowires shows an asymmetric peak at the same position as that of bulk crystalline silicon. ©1998 American Institute of Physics.

History: Received 6 October 1997; accepted 13 February 1998

Permalink: <http://link.aip.org/link/?APPLAB/72/1835/1>

KEYWORDS and PACS

Keywords

silicon, elemental semiconductors, semiconductor quantum wires, nanostructured materials, pulsed laser deposition, stacking faults, twin boundaries, transmission electron microscopy, Raman spectra

PACS

- 81.05.Cy
Materials science Specific materials: fabrication, treatment, testing, and analysis Elemental semiconductors
- 81.05.Ys
Materials science Specific materials: fabrication, treatment, testing, and analysis Nanophase materials
- 81.15.Fg
Materials science Methods of deposition of films and coatings; film growth and epitaxy Laser deposition
- 68.55.Jk
Surfaces and interfaces; thin films and whiskers (structure and nonelectronic properties) Thin film structure and morphology Structure and morphology; thickness
- 61.72.Nn
Structure of solids and liquids; crystallography Defects and impurities in crystals; microstructure Stacking faults and other planar or extended defects
- 78.30.Am
Optical properties, condensed-matter spectroscopy and other interactions of radiation and particles with condensed matter Infrared and Raman spectra Elemental semiconductors and insulators
- YEAR: 1998